

OPIC
OFFICE DE LA PROPRIÉTÉ
INTELLECTUELLE DU CANADA



CIPPO
CANADIAN INTELLECTUAL
PROPERTY OFFICE

(12) (19) (CA) **Demande-Application**

(21) (A1) **2,253,515**
(86) 1998/03/24
(87) 1998/10/01

- (72) AOYAMA, Masatoshi, JP
- (72) TSUTSUMI, Kenichi, JP
- (72) UCHIDA, Minoru, JP
- (71) TORAY INDUSTRIES, INC., JP
- (51) Int. Cl. C08G 63/84

- (30) 1997/03/25 (HEI 9-71870) JP
- (30) 1997/06/04 (HEI 9-146781) JP

- (54) **CATALYSEUR POUR LA PRODUCTION DE POLYESTER, SON
PROCEDE D'OBTENTION ET PROCEDE DE PRODUCTION
DE POLYESTER Y RECOURANT**
- (54) **CATALYST FOR PRODUCING POLYESTER, PROCESS FOR
PRODUCING THE SAME, AND PROCESS FOR PRODUCING
POLYESTER BY USING THE SAME**

(57) L'invention porte sur un catalyseur de production de polyester consistant en une solution de solutés comprenant un composé d'aluminium et un composé alcalin dans de l'eau ou dans un solvant organique ou un mélange des deux, et sur un procédé de production d'un polyester consistant à estérifier ou transestérifier un acide dicarboxylique aromatique ou un de ses dérivés générateur d'ester avec un diol ou l'un de ses dérivés générateur d'ester, puis à polymériser par condensation le produit de réaction résultant et cela en utilisant le catalyseur de polymérisation contenu dans un composé d'aluminium. Ledit catalyseur donne un polyester très facile à mouler et pouvant servir à produire des produits moulés tels que des fibres, des films, des résines, des bouteilles sans poser de problèmes tels que l'encrassement des filières, l'accroissement de la pression de filtrage, la rupture des films, ou des défauts dus à des substances étrangères.

(57) A polymerization catalyst for polyester production which is a solution of solutes comprising an aluminum compound and an alkali compound in water, an organic solvent, or a mixture of both; and a process for producing a polyester which comprises esterifying or transesterifying an aromatic dicarboxylic acid or an ester-forming derivative thereof with a diol or an ester-forming derivative thereof and condensation-polymerizing the resultant reaction product, characterized by using the polymerization catalyst containing an aluminum compound. The catalyst can yield a polyester having excellent moldability and being usable for producing moldings such as fibers, films, resins, bottles, etc., without posing problems such as nozzle fouling, filtering pressure increase, thread breakage, film breakage, and defects caused by foreign substances.



Industrie Canada Industry Canada

BEST AVAILABLE COPY

CA 02253515 1998-11-04

世界知的所有権機関

国際事務局



PCT

特許協力条約に基づいて公開された国際出願

(51) 国際特許分類6 C08G 63/84	AI	(11) 国際公開番号 WO98/42769 (43) 国際公開日 1998年10月1日(01.10.98)
(21) 国際出願番号 PCT/JP98/01275 (22) 国際出願日 1998年3月24日(24.03.98) (30) 優先権データ 特願平9/71870 1997年3月25日(25.03.97) JP 特願平9/146781 1997年6月4日(04.06.97) JP (71) 出願人 (米国を除くすべての指定国について) 東レ株式会社(TORAY INDUSTRIES, INC.)(JP/JP) 〒103-8666 東京都中央区日本橋室町2丁目2番1号 Tokyo, (JP) (72) 発明者 ; および (75) 発明者 / 出願人 (米国についてのみ) 青山雅俊(AOYAMA, Masatoshi)(JP/JP) 〒411-0022 静岡県三島市川原ヶ谷(旭ヶ丘) 459-2 東レ旭が丘アパート4号 Shizuoka, (JP) 堤 賢一(TUTUMI, Kenichi)(JP/JP) 〒411-0033 静岡県三島市文政町2丁目12番6号 三島寮P-216 Shizuoka, (JP) 内田 実(UCHIDA, Minoru)(JP/JP) 〒411-1300 静岡県駿東郡長泉町中土井341番地3 Shizuoka, (JP)		(81) 指定国 CA, CN, ID, KR, US, 欧州特許 (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). 添付公開書類 国際調査報告書
(54) Title CATALYST FOR PRODUCING POLYESTER, PROCESS FOR PRODUCING THE SAME, AND PROCESS FOR PRODUCING POLYESTER BY USING THE SAME (54) 発明の名称 ポリエステル重合触媒とその製造方法およびそれを用いるポリエステルの製造方法 (57) Abstract A polymerization catalyst for polyester production which is a solution of solutes comprising an aluminum compound and an alkali compound in water, an organic solvent, or a mixture of both; and a process for producing a polyester which comprises esterifying or transesterifying an aromatic dicarboxylic acid or an ester-forming derivative thereof with a diol or an ester-forming derivative thereof and condensation-polymerizing the resultant reaction product, characterized by using the polymerization catalyst containing an aluminum compound. The catalyst can yield a polyester having excellent moldability and being usable for producing moldings such as fibers, films, resins, bottles, etc., without posing problems such as nozzle fouling, filtering pressure increase, thread breakage, film breakage, and defects caused by foreign substances.		

FILE ~~RE IN THIS AMEND~~
~~IT~~ ~~RELATION~~

SPECIFICATION

A polyester polymerization catalyst, a production method thereof, and a polyester production method using said catalyst

TECHNICAL FIELD

The present invention relates to a polyester polymerization catalyst, a production method thereof, and a polyester production method using said catalyst. In more detail, the present invention relates to an polyester polymerization catalyst for producing a polyester excellent in processability and color tone, a production method thereof, and a polyester production method using said catalyst.

BACKGROUND ART

Polyesters are used widely in various fields for fibers, films, resins and bottles because of their excellent properties. Among them, polyethylene terephthalate is favorably used since it is excellent in mechanical strength, chemical properties, dimensional stability, etc.

In general, polyethylene terephthalate is produced from terephthalic acid or any of its ester forming derivatives and ethylene glycol. In this case, in commercial processes for producing high molecular polymers, antimony compounds are widely used as polycondensation catalysts. However, polymers

2004年 6月 4日 7時16分

UNUS OFFICE

CA 02253515 1998-11-04

containing any antimony compound have the following several unpreferable properties.

For example, when a polyester obtained by using an antimony catalyst is melt-spun into fibers, it is known that the residue of the antimony catalyst is deposited around the holes of a spinneret. The reason why the residue of the antimony catalyst is deposited is considered to be that antimony exists as antimony glycolate in the polymer and that it is modified near the spinneret, and partially vaporized and dissipated, while a component mainly composed of antimony remains at the spinneret. If the deposit grows, it causes filament breaking, etc. and must be removed from time to time.

Furthermore, the antimony catalyst residue in the polymer is likely to be relatively large grains, and acts as a foreign matter, causing such unpreferable phenomena as filtration pressure rise at the time of processing, filament breaking at the time of spinning, and film breaking at the time of film formation.

Because of the above problems, a polyester having very small or zero in antimony content is being demanded.

To solve the problems, USP 5,512,340 and USP 5,596,069 propose to use an aluminum compound such as aluminum chloride or aluminum hydroxychloride and a cobalt compound together. However, in general, an aluminum compound has such problems that it is unlikely to be dissolved in a glycol such as

ethylene glycol and the polyester reaction system, and if it is added to the polyester reaction system as a polycondensation catalyst, an insoluble foreign matter is formed to cause filament breaking at the time of spinning and film breaking. After all, the problems of antimony cannot be sufficiently avoided.

DISCLOSURE OF THE INVENTION

The object of the present invention is to provide a polyester polymerization catalyst for producing a polyester, which overcomes the disadvantages of the polyester containing said antimony compound and the disadvantages caused when an aluminum compound is used as a polymerization catalyst, and also to provide a production method thereof and a polyester production method using said catalyst.

The present invention relates to a polyester polymerization catalyst, comprising a solution containing an aluminum compound and an alkali compound, with water or an organic solvent or a mixture consisting of water and an organic solvent as the medium, and also relates to a production method thereof and a polyester production method using said catalyst.

THE MOST PREFERRED EMBODIMENTS OF THE INVENTION

The polyester of the present invention is a polymer

synthesized from a dicarboxylic acid or any of its ester forming derivatives and a diol, and is not especially limited as far as it can be used as such products as fibers, films and bottles.

The dicarboxylic acids which can be used here include, for example, dicarboxylic acids such as terephthalic acid, naphthalenedicarboxylic acid, adipic acid, isophthalic acid, sebacic acid, phthalic acid and 4,4'-diphenyldicarboxylic acid, and their ester forming derivatives such as dimethyl esters. The diols which can be used here include ethylene glycol, propylene glycol, butanediol, polyethylene glycol, diethylene glycol, hexamethylene glycol, cyclohexanedimethanol, neopentyl glycol and polypropylene glycol.


The polyesters which can be produced from the above include, for example, polyethylene terephthalate, polytetramethylene terephthalate, polycyclohexylenedimethylene terephthalate, polyethylene-2,6-naphthalenedicarboxylate, polyethylene-1,2-bis(2-chlorophenoxy)ethane-4,4'-dicarboxylate and polypropylene terephthalate. Among them, the present invention is suitable for the most generally used polyethylene terephthalate or a copolyester mainly composed of polyethylene terephthalate.

These polyesters can also have another comonomer copolymerized. The comonomers which can be used here include

other dicarboxylic acids such as adipic acid, isophthalic acid, sebacic acid, phthalic acid and 4,4'-diphenyldicarboxylic acid, and their ester forming derivatives, dihydroxy compounds such as polyethylene glycol, diethylene glycol, hexamethylene glycol, neopentyl glycol and polypropylene glycol, other hydroxycarboxylic acids such as p-(β -hydroxyethoxy)benzoic acid, and their ester forming derivatives.

The aluminum compound in the present invention is not especially limited. However, aluminum organic compounds which can be relatively easily dissolved in a diol such as ethylene glycol used for producing polyethylene terephthalate, and aluminum compounds which are relatively high in aluminum atom content and can provide sufficient catalytic activity with a small amount are preferable.

Examples of the former include the aluminum organic compounds represented by the following general formula (1):



(where R_1 , R_2 and R_3 stand for, respectively independently, an alkyl group, aryl group, acyl group or hydrogen atom, R_4 stands for an alkyl acetoacetate ion or acetylacetone ion, R_1 , R_2 and R_3 are identical or different, subject to the condition that at least one of R_1 , R_2 , R_3 and R_4 does not stand for a hydrogen atom; and l , m , n and o stand for, respectively independently, 0 or a positive number, subject to $l + m + n + o = 3$.)

Concretely they include carboxylic acid salts such as aluminium acetate, aluminium benzoate, aluminium lactate, aluminium laurate, aluminium stearate and aluminum alcholates in which the hydrogen atom of the hydroxyl group of an alcohol is substituted by aluminum element, such as aluminum ethylate, aluminum isopropylate, aluminum tri-n-butyrate, aluminum tri-sec-butyrate, aluminum tri-tert-butyrate and mono-sec-butoxyaluminum diisopropylate, and aluminum chelates in which the alkoxy group of an aluminum alcoholate is partially or wholly substituted by a chelating agent such as an alkyl acetoacetate or acetylacetone, such as ethyl acetoacetate aluminum diisopropylate, aluminum tris(ethyl acetate), alkyl acetoacetate aluminum diisopropylate, aluminum monoacetylacetate bis(ethyl acetoacetate), aluminum tris(acetyl acetate), aluminum monoisopropoxymonooleoxyethyl acetoacetate and aluminum acetylacetate.

Among them, aluminum carboxylates and aluminum alcoholates are especially preferable.

Examples of the latter include hydroxides, chlorides and hydroxychlorides of aluminum. Concretely they include aluminum hydroxide, aluminum chloride, aluminum hydroxychloride, etc. Among them, aluminum hydroxide is especially preferable since the polymer obtained is good in heat resistance and color tone since it does not contain any halogen atom. The aluminum acetate of the present invention

0004E SF 4E 17:17:18

JULIUS OFFICE


CA 02153515 1998-11-04

can also be generally marketed so-called basic aluminum acetate.

The alkali compounds which can be used in the present invention refer to alkali compounds in a wide sense, i.e., the whole of a group consisting of alkali metal hydroxides, alkaline earth metal hydroxides, and also alkali metal carbonates, ammonia, amines and their derivatives, for example, as stated in Dictionary of Physicochemistry (Rikagaku-Jiten in Japanese) (3rd edition, revised and enlarged, Iwanami Shoten, 1982), etc.

In the present invention, among these alkali compounds, nitrogen-containing compounds are preferable since the polyester compositions obtained are especially good in color tone.


Preferable nitrogen-containing compounds of the present invention include, for example, those represented by the following formulae (2) and (3):



[where R_1 , R_2 and R_3 stand for, respectively independently, a hydrogen atom, alkyl group, aryl group and allyl group.]

R₂

|



|

R₄

[where R₁, R₂, R₃ and R₄ stand for, respectively independently, a hydrogen atom, alkyl group, aryl group and allyl group.]

Concretely the compounds of formula (2) include ammonia, diethylamine, trimethylamine, triethylamine, tripropylamine, tributylamine, etc. The compounds of formula (3) include tetramethylammonium hydroxide, tetraethylammonium hydroxide, tetrapropylammonium hydroxide, tetrabutylammonium hydroxide, trimethylbenzylammonium hydroxide, etc.

Other compounds than those represented by the formulae (2) and (3) which can be used here include derivatives of the compounds represented by the formulae (2) and (3), ethylenediamine, tetraethylenediamine, hexamethylenediamine, pyridine, quinoline, pyrrolidine, pyrrolidone, piperidine, etc.

As the nitrogen-containing compounds of the present invention, among the above compounds, tertiary amine compounds and quaternary ammonium compounds are preferable since the amount of the foreign matter produced in the polyester composition obtained is especially small. Furthermore, compounds which are volatilized at 280°C or lower are preferable since the amount remaining in the finally obtained polyester composition is small to improve the color tone of the polyester composition. The compounds include tertiary

amine compounds such as trimethylamine, triethylamine, tripropylamine and tributylamine, and quaternary ammonium compounds such as tetramethylammonium hydroxide, tetraethylammonium hydroxide, tetrapropylammonium hydroxide, tetrabutylammonium hydroxide and trimethylbenzylammonium hydroxide.

The aluminum compound of the present invention must be mixed with a solvent containing the alkali compound before it is added to the reaction system of the polyester.

The inventors found that when an aluminum compound generally likely to form an insoluble foreign matter in the polyester is used as a polyester polymerization catalyst, if the compound is finely dispersed in a solvent containing the alkali compound before it is added to the reaction system, the compound is unlikely to form any insoluble foreign matter still after it is added to the reaction system. Thus, the present invention has been completed.

It is especially preferable to mix the alkali compound with water for making an aqueous solution and then to mix the aluminum compound with the aqueous solution, since the aluminum compound can be homogeneously dispersed or dissolved in the aqueous solution, to inhibit the production of the foreign matter in the polyester. Furthermore, it is preferable to dilute the aqueous solution containing the aluminum compound by the diol component of the polyester such

as ethylene glycol before the aqueous solution is added to the reaction system, since the local concentration due to sudden temperature change is unlikely to occur.

When the aluminum compound is mixed with such a mixture with the alkali compound contained in water or an organic solvent or a mixture consisting of water and an organic solvent, it is preferable that the concentration of the alkali compound is 0.5 to 50 wt%, especially 1 to 40 wt% based on the amount of the water or the organic solvent or the mixture consisting of water and an organic solvent, since the aluminum compound added later can be more easily dispersed or dissolved.

It is preferable that the solution to be added to the polyester reaction system contains 0.05 to 20 wt%, as aluminum atoms, of the aluminum compound and 0.05 to 30 wt% of the alkali compound, since the amount of the foreign matter in the obtained polyester is especially small. If the alkali compound is a nitrogen-containing compound, it is especially preferable that the concentration of the nitrogen-containing compound is 0.05 to 20 wt% as nitrogen atoms, since the amount of the foreign matter in the obtained polyester is small.

The polyester polymerization catalyst used in the present invention can be used in polycondensing the product obtained by either the esterification reaction between an aromatic dicarboxylic acid and a diol, or the ester interchange

reaction between an ester forming derivative of an aromatic dicarboxylic acid and a diol.

It is preferable that the aluminum compound of the present invention is added to ensure that the weight of aluminum atoms may be 5 to 500 ppm based on the weight of the obtained polyester. To obtain sufficient catalytic activity, hence to obtain a polymer with a higher molecular weight and a product with sufficient strength, it is preferable that the amount added is 5 ppm or more. Furthermore, to prevent the likelihood to produce the foreign matter, the remarkable rise of filtration pressure at the time of processing and the tendency to worsen the polymer color tone, 500 ppm or less is preferable. A more preferable range is 50 to 400 ppm, and a further more preferable range is 80 to 350 ppm.

It is preferable to add the alkali compound of the present invention by 50 to 5000 ppm based on the weight of the obtained polyester. In view of the effect to inhibit the production of any foreign matter, 50 ppm or more is preferable, and to prevent the worsening of the color tone of the obtained polyester, 5000 or less is preferable. A more preferable range is 70 to 3000 ppm, and an especially preferable range is 80 to 1000 ppm. Among the alkali compounds which can be used in the present invention, some are likely to be dissipated during polymerization reaction, and if any of the compounds is used, the compound is not required to

perfectly remain in the finally obtained polymer.

The polymerization catalyst containing aluminum of the present invention can be added to the reaction system at any moment when the polyester is produced, but it is preferable that the molar ratio (the molar ratio of the aromatic dicarboxylic acid or any of its ester forming derivatives to the diol) in the reaction system is 1.25 to 2.0 when the catalyst is added, since the production of the foreign matter can be especially inhibited.

In the case of ester interchange reaction, a molar ratio of about 2.0 is usually adopted, and in this case, the polymerization catalyst containing the aluminum compound can be added as it is, to the reaction system. On the other hand, in the case of esterification reaction, a molar ratio of less than 1.25 may be adopted. So, before the aluminum compound is added, it is preferable to add, for example, a diol by 0.1 to 1.5 times the amount of the aromatic dicarboxylic acid, for satisfying said condition.

In the present invention, it is preferable to use a cobalt compound together, since the polycondensation reaction progresses more quickly and the color tone of the obtained polyester is improved.

The cobalt compound of the present invention is not especially limited, but can be selected, for example, from cobalt acetate tetrahydrate, cobalt nitrate, cobalt chloride,

cobalt acetylacetonate, cobalt naphthenate, etc.

It is preferable that the amount of the cobalt compound added is 0.5 to 20 as a molar ratio of aluminum atoms to cobalt atoms (Al/Co). If the molar ratio is in this range, the effects of improving the polymerization activity and the polymer color tone are high, and the heat resistance can also be good. A more preferable range is 1 to 15, and a further more preferable range is 2 to 10.

In the present invention, a polymerization catalyst like a titanium compound such as tetrabutyl titanate or tetrapropyl titanate or an antimony compound such as antimony trioxide or antimony acetate can be used by a small amount together with the aluminum compound as far as the effects intended in the present invention are not impaired.

If the amount of the titanium compound added is smaller than the amount of aluminum atoms added and 50 ppm or less as titanium atoms based on the amount of the polyester, the polymerization time can be shortened, and the color tone of the obtained polymer is in a permissible range. More preferable is 20 ppm or less, and further more preferable is 10 ppm or less.

If the amount of the antimony compound added is smaller than the amount of aluminum atoms added and 50 ppm or less as antimony atoms based on the amount of the polyester, filament breaking at the time of spinning and film breaking at the time

of film formation can be prevented, and in the case of bottles, etc., the transparency is in a permissible range. More preferable is 30 ppm or less, and further more preferable is 10 ppm or less.

The method for producing the polyester of the present invention is described below for a case of polyethylene terephthalate.

High molecular polyethylene terephthalate used for fibers, films, resins or bottles, etc. is usually produced according to either of the following processes; (1) a process comprising the steps of treating terephthalic acid and ethylene glycol as raw materials at about 240 to 270°C at atmospheric pressure or higher pressure for obtaining low molecular polyethylene terephthalate or oligomer directly by esterification reaction, and furthermore heating it to about 290°C while reducing the pressure of the system to 133 Pa or less for polycondensation reaction, to obtain the intended high molecular polymer, and (2) a process comprising the steps of heating a reaction system containing dimethyl terephthalate (DMT) and ethylene glycol as raw materials from 150°C to 240°C at atmospheric pressure, to obtain a oligomer by ester interchange reaction, and effecting polycondensation reaction as described in (1) to obtain the intended high molecular polymer.

The esterification reaction can be effected even without any catalyst, but the ester interchange reaction is usually

effected using a compound of manganese, calcium, magnesium, zinc or lithium, etc. as a catalyst and adding a phosphorus compound to inactivate the catalyst used for said reaction, after substantial completion of ester interchange reaction.

In the production method of the present invention, a specific polymerization catalyst containing an aluminum compound and an alkali compound of the present invention is added to the oligomer obtained in the beginning or former half of the process (1) or (2), and then, the polycondensation reaction in the latter half is effected to obtain high molecular polyethylene terephthalate. Furthermore, the reaction can be effected in batch operation, semi-batch operation or continuous operation.

The methods for measuring and evaluating properties in the present invention are described below.

(1) Intrinsic viscosity of polymer $[\eta]$

Measured with orthochlorophenol as the solvent at 25°C.

(2) Metal content of polymer

Obtained according to the fluorescent X-ray method.

(3) Color tone of polymer

Pellets were used as a polymer sample, and the light reflected from the sample was measured using a color difference meter (SM Color Computer Model SM-3) produced by Suga Shikenki K.K. and expressed according to the Hunter expression method (values L, a and b).

(4) Amount of carboxyl end groups of polymer

According to Maurice et al.'s method [Anal. Chim. Acta, 22, p. 363 (1960)].

(5) Strength and elongation of fibers

An S-S curve was obtained by Tensilon Tensile Tester produced by Toyo Baldwin at a sample length of 250 mm at a tensile speed of 300 mm/min, to calculate the strength and elongation.

The present invention is described below concretely in reference to examples, but is not limited thereto or thereby.

Example 1

Ten parts of aluminum hydroxide were added to 100 parts of an aqueous solution containing 20 wt% of tetraethylammonium hydroxide, and the mixture was stirred to obtain a homogeneous aqueous solution. The aqueous solution was diluted by 90 parts of ethylene glycol, to produce a homogeneous ethylene glycol solution containing tetraethylammonium hydroxide, water and aluminum hydroxide, as a solution containing 1.7 wt%, as aluminum atoms, of an aluminum compound and 10 wt% of an alkali compound.

On the other hand, a polyester was produced from highly pure terephthalic acid and ethylene glycol according to a conventional method. That is, an oligomer produced beforehand was molten and stirred at atmospheric pressure at 250°C, and a

slurry consisting of highly pure terephthalic acid and ethylene glycol was gradually added to the oligomer, for esterification reaction, to finally obtain an oligomer not containing a catalyst. To the oligomer, the ethylene glycol solution containing tetraethylammonium hydroxide, water and aluminum hydroxide produced beforehand was added to keep the aluminum atom content at 50 ppm in the finally obtained polyester. The molar ratio of the reaction system in this case was 1.50. Furthermore, cobalt acetate tetrahydrate was added to keep the cobalt atom content at 20 ppm. The oligomer mixture was stirred at 30 rpm, while the reaction system was gradually heated from 250°C to 285°C, with the pressure reduced to 40 Pa. Both the time taken to reach the final temperature and the time taken to reach the final pressure were 60 minutes. When a predetermined stirring torque was reached, the reaction system was purged by nitrogen and returned to atmospheric pressure, to stop the polycondensation reaction. The product obtained was discharged into cold water as a strand which was immediately cut to obtain polyester pellets.

The obtained polymer was 0.68 in intrinsic viscosity, 29 equivalents/ton in the amount of carboxyl end groups and $L = 59$, $a = 0.6$ and $b = 5.0$ in color tone. The polymer was analyzed by the fluorescent X-ray method, and the aluminum atom content was found to be 50 ppm.

As stated above, the polymerization reactivity was good

and the polyester pellets to obtained were also good in their properties.

The pellets were dried, supplied into an extruder type spinning machine and melt-spun at a spinning temperature of 295°C. In this case, a metallic nonwoven fabric with an absolute filtration accuracy of 10 μm was used as the filter, and the spinneret used had a round hole with a diameter of 0.6 mm. The yarn discharged from the spinneret was gradually cooled in a heating cylinder with a length of 30 cm, an inner diameter of 25 cm and a temperature of 300°C, and chimney cooling air was applied to cool and solidify it. It was oiled and taken up at a take-up speed of 550 m/min. The undrawn yarn was drawn at 95°C with the drawing ratio changed properly to achieve an elongation of 14 to 15% in the intended drawn yarn. Then, it was heat-treated at 220°C at a relax rate of 2.0%, to obtain a drawn yarn.

In the melt spinning process, little filtration pressure rise was observed at the time of spinning, and the yarn breaking little occurred at the time of drawing, to show that the polymer was good in processability.

The results are shown in Table 1.

Examples 2 to 12 and Comparative Examples 1 to 3

Polymers were produced as described in Example 1, except that the kinds and quantities of the metal compound and the alkali compound were changed, and melt-spun. The results are

shown in Tables 1 and 2.

The polymers of the present invention were good in physical properties and melt spinning process. However, when a catalyst free from any alkali compound or antimony trioxide only was used for polymerization, the filtration pressure rose remarkably in the melt spinning process, and yarn breaking occurred frequently, to show poor processability.

The filtration pressure rise and yarn breaking in spinning are caused by various causes, and the foreign matter in the polymer is also one of the main causes. In the examples, no or little filtration pressure rise during spinning was expressed as good. In Examples 6 and 7, some filtration pressure rise was observed, but it was judged to conform to the tolerance since it did not affect the normal filter exchange period. No or little yarn breaking in the examples was also expressed as good. The yarn breaking in Examples 6 and 7 occurred at the upper limit of an acceptable range, and was judged to be tolerable in view of operation convenience.

CA 02233315 1998-11-04

Table 1

	Metal compounds			Polycondensation reaction time	Properties of polymer					Spinnability	
	Compounds used	Amount added based on the amount of polymer (ppm)	Al/Co		Intrinsic viscosity	Amount of carbonyl end groups (equivalents/ton)	Value L	Value a.	Value b	Filtration pressure	Yarn breaking
Example 1	Aluminum hydroxide Tetraethylammonium hydroxide Cobalt acetate tetrahydrate	Al=50 Alkali=200 Co=20	2.5	2:50	0.68	29	59	0.6	5.0	Good	Good
Example 2	Basic aluminum acetate Tetraethylammonium hydroxide	Al=50 Alkali=736	-	3:00	0.65	23	59	-0.6	9.5	Good	Good
Example 3	Aluminum chloride Tetraethylammonium hydroxide	Al=60 Alkali=1050	-	2:50	0.67	40	53	0.6	14.0	Good	Good
Example 4	Aluminum chloride Tetraethylammonium hydroxide Cobalt acetate tetrahydrate	Al=45 Alkali=1500 Co=20	2.3	2:40	0.68	42	51	1.5	12.0	Good	Good
Example 5	Aluminum hydroxide Tetraethylammonium hydroxide	Al=70 Alkali=420	-	3:00	0.65	19	61	-0.2	9.0	Good	Good
Example 6	Basic aluminum acetate Tetraethylammonium hydroxide Antimony trioxide	Al=60 Alkali=1260 Sb=40	-	2:40	0.70	20	53	-0.5	8.5	a)	b)
Example 7	Aluminum hydroxide Triethylamine	Al=60 Alkali=530	-	3:00	0.63	21	63	-0.2	7.0	a)	b)

a) Filtration pressure rose to some extent, but within tolerance.

b) Some yarn breaking occurred, but within tolerance.

c) The "Alkali" in "Amount added based on the amount of polymer (ppm)" means an alkali compound.

CA 02253515 1998-11-04

Table 2

	Metal compounds			polycondensation reaction time	Properties of polymer				Spinnability	
	Compounds used	Amount added based on the amount of polymer (ppm)	Al/Co		Intrinsic viscosity	Amount of carboxyl and groups (equivalents/ton)	Value L	Value a	Value b	Filtration pressure
Example 8	Aluminum hydroxychloride Tetraethylammonium hydroxide Cobalt acetate	Al=60 Alkali=6300 Co=5	12	0.62	42	52	0.6	16.0	Good	Good
Example 9	Basic aluminum acetate Triethylamine Cobalt acetate	Al=30 Alkali=5300 Co=50	0.6	0.66	40	60	1.0	0.5	Good	Good
Example 10	Aluminum hydroxide Sodium hydroxide	Al=80 Alkali=60	-	0.64	21	60	-0.2	9.5	a)	a)
Example 11	Aluminum acetylacetate Tetraethylammonium hydroxide	Al=150 Alkali=740	-	0.69	21	62	-0.1	7.0	Good	Good
Example 12	Aluminum isopropoxide Tetraethylammonium hydroxide Tetraethyl titanate	Al=60 Alkali=420 Ti=3	-	0.70	30	53	-0.1	10.0	Good	Good
Comparative Example 1	Aluminum hydroxide	Al=70	-	0.59	23	63	-0.3	7.0	Filtration pressure remarkably rose	Yarn breaking occurred frequently
Comparative Example 2	Antimony trioxide	8B=300	-	0.66	20	46	-0.6	4.6	Filtration pressure remarkably rose	Yarn breaking occurred frequently
Comparative Example 3	Aluminum chloride Cobalt acetate tetrahydrate	Al=60 Co=20	3	0.70	43	51	-0.2	10.0	Filtration pressure remarkably rose	Yarn breaking occurred frequently

a) Filtration pressure rose to some extent, but within tolerance.

b) Some yarn breaking occurred, but within tolerance.

c) The "Alkali" in "Amount added based on the amount of polymer (ppm)" means an alkali compound.

CLAIMS

1. A polyester polymerization catalyst, comprising a solution containing an aluminum compound and an alkali compound, with water or an organic solvent or a mixture consisting of water and an organic solvent as the medium.

2. A polyester polymerization catalyst, according to claim 1, wherein the aluminum compound is contained by 0.05 to 20 wt% as aluminum atoms and the alkali compound is contained by 0.5 to 30 wt%.

3. A polyester polymerization catalyst, according to claim 1 or 2, wherein the aluminum compound is an aluminum organic compound represented by the following general formula:



(where R_1 , R_2 and R_3 stand for, respectively independently, an alkyl group, aryl group, acyl group or hydrogen atom, R_4 stands for an alkyl acetoacetate ion or acetylacetone ion, R_1 , R_2 and R_3 are identical or different, subject to the condition that at least one of R_1 , R_2 , R_3 and R_4 does not stand for a hydrogen atom; and l , m , n and o stand for, respectively independently, 0 or a positive number, subject to $l + m + n + o = 3$.)

4. A polyester polymerization catalyst, according to claim 3, wherein the aluminum organic compound is at least one selected from a group consisting of aluminum alcholates and aluminum carboxylates.

5. A polyester polymerization catalyst, according to claim 1 or 2, wherein the aluminum compound is at least one compound selected from a group consisting of hydroxides, chlorides and hydroxychlorides of aluminum.
6. A polyester polymerization catalyst, according to any one of claims 1 through 5, wherein the alkali compound is a nitrogen-containing compound.
7. A polyester polymerization catalyst, according to claim 6, wherein the nitrogen-containing compound is a tertiary amine compound or a quaternary ammonium compound.
8. A method for producing a polyester polymerization catalyst stated in any one of claims 1 through 7, comprising the steps of letting water or an organic solvent or a mixture consisting of water and an organic solvent contain an alkali compound, and adding an aluminum compound to the mixture.
9. A method for producing a polyester, in which a product obtained by the esterification reaction or ester interchange reaction between an aromatic dicarboxylic acid or any of its ester forming derivatives and a diol is polycondensed to produce a polyester, comprising the step of using the polymerization catalyst stated in any one of claims 1 through 7, to ensure that the amount of the aluminum compound is 5 to 500 ppm as aluminum atoms based on the amount of the obtained polyester.
10. A method for producing a polyester, according to claim 9,

based on the amount of the polyester.

**Smart & Biggar
Ottawa, Canada
Patent Agents**

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.